

AD-A131 842

IONIC CONDUCTIVITY IN LITHIUM HEXAOXOMETALLATE SOLID
SOLUTIONS(U) RUTGERS - THE STATE UNIV NEW BRUNSWICK NJ
DEPT OF CHEMISTRY E NOMURA ET AL. 26 JUL 83 TR-1

1/


UNCLASSIFIED

N00014-82-K-0317

F/G 7/4

NL

												END		
												DATE		
												FILED		
												9-83		
												DTIC		



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

12

OFFICE OF NAVAL RESEARCH

Contract N00014-82-K-0317

Task No. NR 627-802

TECHNICAL REPORT NO. 1

Ionic Conductivity in Lithium Hexaoxometallate

Solid Solutions

By

E. Nomura and M. Greenblatt

Prepared for Publication

in the

Conference Proceedings on "High Temperature

Solid Oxide Electrolytes" Brookhaven National

Laboratory, Upton, New York

Rutgers, The State University of New Jersey
Chemistry Department
New Brunswick, N. J.

July 26, 1983

Reproduction in whole or in part is permitted for
any purpose of the United States Government.

This document has been approved for public release
and sale; its distribution is unlimited.

83 08 22.018

ADA 131842

DTIC FILE COPY

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) IONIC CONDUCTIVITY IN LITHIUM HEXAOXOMETALLATE SOLID SOLUTIONS		5. TYPE OF REPORT & PERIOD COVERED Technical June 1, 1982-July 31, 1983
7. AUTHOR(s) E. Nomura and M. Greenblatt		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry Rutgers, The State University of New Jersey New Brunswick, NJ 08903		8. CONTRACT OR GRANT NUMBER(s) N00014-82-K-0317
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 N. Quincy Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE August 9, 1983
		13. NUMBER OF PAGES 15
		15. SECURITY CLASS. (of this report) Unclassified
		18a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Prepared for Proceedings of High Temperature Solid Oxide Electrolytes Conference		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) lithium ion conductivity, solid electrolytes		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Lithium ion conductivity in solid solutions formed between Li_7TaO_6 , $\text{Li}_7\text{M}^{\text{V}}\text{O}_6$ ($\text{M}^{\text{V}} = \text{Nb, Bi}$) and Li_8ZrO_6 has been measured as a function of temperature and composition using complex impedance method. The samples prepared were $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$, $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$ and $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$. At 200°C , the conducti- vities of $\text{Li}_7\text{Ta}_{0.7}\text{Nb}_{0.3}\text{O}_6$, $\text{Li}_7\text{Ta}_{0.6}\text{Bi}_{0.4}\text{O}_6$ and $\text{Li}_{7.4}\text{Ta}_{0.6}\text{Zr}_{0.4}\text{O}_6$ are $4.3 \times 10^{-4} (\Omega\text{cm})^{-1}$, $3.0 \times 10^{-4} (\Omega\text{cm})^{-1}$ and $4.0 \times 10^{-4} (\Omega\text{cm})^{-1}$, respectively.		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Accepted for publication
J. Electrochem. Soc.
1979

X

IONIC CONDUCTIVITY IN LITHIUM HEXAOXOMETALLATE SOLID SOLUTIONS

E. Nomura and M. Greenblatt
Department of Chemistry
Rutgers, The State University of New Jersey
New Brunswick, N.J. 08903

A

ABSTRACT

Lithium ion conductivity in solid solutions formed between Li_7TaO_6 , $\text{Li}_7\text{M}^{\text{V}}\text{O}_6$ ($\text{M}^{\text{V}} = \text{Nb}, \text{Bi}$) and Li_8ZrO_6 has been measured as a function of temperature and composition using complex impedance method. The samples prepared were $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$, $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$ and $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$. At 200°C , the conductivities of $\text{Li}_7\text{Ta}_{0.7}\text{Nb}_{0.3}\text{O}_6$, $\text{Li}_7\text{Ta}_{0.6}\text{Bi}_{0.4}\text{O}_6$ and $\text{Li}_{7.4}\text{Ta}_{0.6}\text{Zr}_{0.4}\text{O}_6$ are $4.3 \times 10^{-4} (\Omega\text{cm})^{-1}$, $3.0 \times 10^{-4} (\Omega\text{cm})^{-1}$ and $4.0 \times 10^{-4} (\Omega\text{cm})^{-1}$, respectively.

INTRODUCTION

There is considerable interest in developing solid lithium ion conductors for utilization in high energy density battery systems. This has led to a search for new solid electrolytes exhibiting high lithium ion conductivity and has stimulated interest in developing a fundamental understanding of ionic transport in solids⁽¹⁻³⁾.

The compounds of lithium hexaoxometallates, formulated as Li_nMO_6 ; $n = 6, 7$ or 8 , $\text{M} = \text{IV}, \text{V}$ or VI group element, have a pseudo two dimensional structure and high lithium ion conductivity⁽⁴⁾. The structure of Li_nMO_6 is characterized by octahedral sheets of CdI_2 -type, between which 6 Li^+ are inserted in a tetrahedral environment as



$$a+b+c = 3$$

\square : vacancy


Among the lithium hexaoxometallates, Li_7TaO_6 (i.e. $\text{Li}_6(\text{LiTa}\square)\text{O}_6$) is the best lithium conductor with $\sigma_{200} = 5 \times 10^{-4} (\Omega\text{cm})^{-1}$ and $\sigma_{\text{RT}} = 4.3 \times 10^{-8} (\Omega\text{cm})^{-1}$ ⁽⁴⁾.

It has been shown that the activation energy for Li^+ diffusion in the tetrahedral sites between the layers is significantly larger than that for the octahedral lithium ion in the layers⁽⁵⁾. Thus by altering the lithium content and/or the vacant sites in the layers higher ionic conductivities might be achieved. We have examined the effect of increased Li^+ content by partial substitution of tantalum ions with Zr^{4+} to yield $\text{Li}_6(\text{Li}_{1+x}\text{Ta}_{1-x}\text{Zr}_x \square_{1-x})\text{O}_6$. We have also attempted to look at the effect of decreased Li^+ content (or increased vacancies) in the layers by studying the conductivities of samples with substituted divalent cations (e.g. $\text{Li}_6(\text{Li}_{1-2x}\text{Mg}_x\text{Ta} \square_{1+x})\text{O}_6$), however our results are inconclusive on this system due to difficulties in obtaining single phase compounds.

Alternatively we hoped to obtain higher lithium conductivities in this system by partial substitution of the tantalum ions with other group V metal ions of larger ionic radii in order to optimize the channel size of the framework structure for lithium diffusion. In this paper we report the results of the lithium conductivity in: $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$, $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$, $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$.

EXPERIMENTAL

Li_2O was obtained by thermal decomposition of anhydrous Li_2O_2 in vacuum at 450°C for 6 hours. Other starting materials were reagent grade Nb_2O_5 , Ta_2O_5 , Bi_2O_3 and ZrO_2 . Mixtures of appropriate composition were thoroughly mixed using agate mortar in a He dry box. For example, $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$ and $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$ were prepared from Li_2O , Ta_2O_5 and Nb_2O_5 , and Li_2O , Ta_2O_5 and Bi_2O_3 , respectively, according to the following equation



The mixtures were pressed into cylindrical pellets $3/8$ " diameter and about 0.2" thick at 15 kpsi. The pressed pellets were transferred to high purity alumina crucibles, were embedded in excess Li_2O powder in order to prevent Li_2O losses, and were heated at 650°C for 18 hours in air. After cooling, the pellets were crushed and examined by X-ray powder diffraction using a Norelco diffractometer with Ni filtered copper radiation. Lithium content was determined by atomic absorption spectrophotometric methods.

Pellet samples for ionic conductivity measurements were prepared by pressing to $1/4$ " diameter and about 0.15" thickness at 30 kpsi followed by sintering at 950°C for 18 hours in air and quenching in air. Again, Li_2O loss was minimized by covering the pellets with Li_2O powder during the sintering process. The X-ray diffraction pattern and lithium content of the sintered samples were checked to confirm the identity and composition of the phases present. Weight loss was not observed after sintering. The density of the sintered pellets were about 85% of theoretical value. Both surfaces of the pellets were polished using silicon carbide (#400) paper and sputtered with about $1\mu\text{m}$ of gold followed by a coating of silver paint (Engelhard #16).

The device for the conductivity measurement is shown in Fig. 1. Platinum contact leads were made by spot welding pieces of platinum foil of $10 \times 10 \text{ mm}^2$ to platinum wires. Two discs of α -alumina of 10 mm diameter and 3 mm thickness were used for insulating the materials. Contact between the sample electrode (sputtered gold and painted silver) and the platinum lead was made

Fig. 1
Device for conductivity measurement

- | | |
|---------------------------|-------------------------|
| 1. sample Pellet | 3. platinum lead |
| 2. α -alumina disc | 4. stainless steel disc |
| 5. screw | |

Fig. 2
Circuit diagram for AC conductivity measurement

- | | |
|-------------------------|--|
| A. tuned amplifier | PS. phase shifter |
| M. mixer | I. integrator |
| R _x . sample | R _{std} . standard resistance |

by tightening the screw (Fig. 1). The AC conductivity measurements were made using ionically blocking electrodes. The schematic electrical circuit diagram of the AC conductivity measurement is shown in Fig. 2. Lock-in amplifier (PAR Model 128A) was used as a phase sensitive detector and a Hewlett-Packard Model 200 CDR was used as a signal generator. The frequency range used was between 5 HZ and 100 KHZ. The measurement temperature was from room temperature to 250°C in air.


RESULTS AND DISCUSSIONS

Li₇TaO₆ ~~~~~

The ionic conductivity of $\sigma_{200} \approx 5 \times 10^{-4} (\Omega \text{ cm})^{-1}$ and activation energy of 0.66 eV of Li₇TaO₆ have been measured by C. Delmas et al⁽⁴⁾. We have also measured the conductivity of sintered pellets of Li₇TaO₆. Fig. 3 shows the conductivity, σ versus $1/T$ of Li₇TaO₆. Different activation energies corresponding to a lower and higher temperature regions are observed. In the higher temperature region, the deviation of ionic conductivity between different pellets is small (which is also a measure of the reliability of the data) and the activation energy is 0.67 eV. In the lower temperature region, the ionic conductivity of different pellets differ more significantly but the activation energies are the same (0.46 eV). The change in the slope of the σ vs $1/T$ plot of Li₇TaO₆ probably corresponds to a transition from extrinsic to intrinsic conductivity regions; then the variations in the ionic conductivities of different samples in the lower temperature region can be explained by differences in defect concentrations or particle packing from sample to sample.

Fig. 3

The temperature dependence of
the conductivity of Li₇TaO₆



The X-ray diffraction patterns of the solid solutions prepared were identical to that of Li_7TaO_6 except for the shifts in 2θ . The lattice parameters calculated for a hexagonal unit cell increased with increasing values of x for $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$ and for $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$; $a = 5.42\text{\AA}$, $c = 15.17\text{\AA}$ for $\text{Li}_7\text{Ta}_{0.6}\text{Nb}_{0.4}\text{O}_6$ and $a = 5.44\text{\AA}$, $c = 15.23\text{\AA}$ for $\text{Li}_7\text{Ta}_{0.6}\text{Bi}_{0.4}\text{O}_6$. The lattice parameters of Li_7TaO_6 , Li_7NbO_6 and Li_7BiO_6 are $a = 5.39\text{\AA}$; $c = 15.11\text{\AA}$; $a = 5.40\text{\AA}$; $c = 15.12\text{\AA}$; and $a = 5.50\text{\AA}$, $c = 15.45\text{\AA}$, respectively⁽⁷⁾. It is clear that the lattice parameters of $\text{Li}_7\text{Ta}_{0.6}\text{Nb}_{0.4}\text{O}_6$ are larger than those of either of the component compounds, Li_7TaO_6 and Li_7NbO_6 , while the lattice parameters of $\text{Li}_7\text{Ta}_{0.6}\text{Bi}_{0.4}\text{O}_6$ are intermediate between those of Li_7TaO_6 and Li_7BiO_6 . The variation of lattice parameters with x in $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$ and $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$ is shown in Fig. 4. The bismuth substituted phases appear to obey Vagard's law while the $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$ system does not. This suggests that there might be a new phase close to the $\text{Li}_7\text{Ta}_{0.6}\text{Nb}_{0.4}\text{O}_6$ composition.

The ionic conductivities of $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$ are shown in Fig. 5. The ionic conductivities increase from $1.1 \times 10^{-4} (\Omega \text{ cm})^{-1}$ for $x = 0.0$ to $4.3 \times 10^{-4} (\Omega \text{ cm})^{-1}$ for $x = 0.3$ at 200°C and decrease as x is increased further (Fig. 5). The activation energy of conduction is 0.63 eV for $\text{Li}_7\text{Ta}_{0.7}\text{Nb}_{0.3}\text{O}_6$, somewhat smaller than the 0.67 eV observed for Li_7TaO_6 .

The ionic conductivities of $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$ phases are shown in Fig. 6. The ionic conductivities increase to $3.0 \times 10^{-4} (\Omega \text{ cm})^{-1}$ at 200°C at $x = 0.4$. The activation energy for conduction is 0.60 eV in $\text{Li}_7\text{Ta}_{0.7}\text{Bi}_{0.3}\text{O}_6$.

Fig. 4
Lattice parameters of
 $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6(0)$ and
 $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6(0)$

Fig. 5
The temperature dependence of the
conductivity of $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$
phases

Fig. 6
The temperature dependence of the
conductivity of $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$
phases

In the $\text{Li}_7\text{Ta}_{1-x}\text{Nb}_x\text{O}_6$ and $\text{Li}_7\text{Ta}_{1-x}\text{Bi}_x\text{O}_6$ phases the observed increase in ionic conductivity and decrease in activation energy at $x = 0.3$ and 0.4 respectively compared to Li_7TaO_6 is clearly due to optimizing the channel size for lithium diffusion at these compositions.

$\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$

The powder X-ray diffraction pattern of $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$ is similar to that of Li_7TaO_6 . The lattice parameters increased with increasing values of x ; $a = 5.44\text{\AA}$ and $c = 15.25\text{\AA}$ were found for $\text{Li}_{7.4}\text{Ta}_{0.6}\text{Zr}_{0.4}\text{O}_6$.

The ionic conductivities of $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$ are shown in Fig. 7. The change in the slope of σ vs $1/T$ curves of $\text{Li}_{7.1}\text{Ta}_{0.9}\text{Zr}_{0.1}\text{O}_6$ corresponds most likely again to the transition from extrinsic to intrinsic mechanism of conductivity. The activation energies are 0.50 eV and 0.60 eV in the lower and higher temperature regions respectively. A similar change in the slope of the σ vs $1/T$ plot of $\text{Li}_{7.3}\text{Ta}_{0.7}\text{Zr}_{0.3}\text{O}_6$ is observed at a higher temperature, suggesting that the increased conductivity observed in the $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$ phases is due to the larger concentration of mobile Li^+ ions. $\text{Li}_{7.4}\text{Ta}_{0.6}\text{Zr}_{0.4}\text{O}_6$ is in the region of extrinsic conductivity for the entire range of temperature measured.

In Table 1, we summarize conductivity data for the best Li solid electrolytes. It may be concluded that solid solutions of lithium hexaoxometallates are also members of good lithium ion conducting solid electrolytes.

Fig. 7

The temperature dependence of conductivity of $\text{Li}_{7+x}\text{Ta}_{1-x}\text{Zr}_x\text{O}_6$ phases

Table 1 Conductivity data for Li compounds.

Compounds	σ_{RT} (Ωcm) ⁻¹	σ_{200} (Ωcm) ⁻¹	Activation Energy (eV)	Temp. Range (°C)	Ref.
Li- β -Al ₂ O ₃	1.3 x 10 ⁻⁴	2.0 x 10 ⁻³	0.19 0.36	-100 - 180 180 - 800	8
Li ₁₄ Zn(GeO ₄) ₄ (LISICON)		1.7 x 10 ⁻⁴	0.50	50 - 300	9
Li ₄ B ₇ O ₁₂ Cl _{0.68} Br _{0.32}	5.4 x 10 ^{-7*}	6.5 x 10 ⁻⁴	0.53	50 - 230	1
Li _{3.75} Si _{0.75} P _{0.25} O ₄	4.8 x 10 ^{-7*}	1.0 x 10 ⁻³	0.60	30 - 230	1
Li _{4.4} Si _{0.6} Al _{0.4} O ₄	2.8 x 10 ^{-7*}	7.6 x 10 ⁻⁴	0.58	70 - 230	1
Li _{4.6} Al _{0.6} Si _{0.4} O ₄		7.7 x 10 ⁻⁵	0.68	85 - 230	1
Li ₇ Ta _{0.7} Nb _{0.3} O ₆	7.3 x 10 ^{-8*}	4.3 x 10 ⁻⁴	0.63	80 - 230	this work
Li ₇ Ta _{0.6} Bi _{0.4} O ₆	7.3 x 10 ^{-8*}	3.0 x 10 ⁻⁴	0.60	50 - 230	this work
Li _{7.4} Ta _{0.6} Zr _{0.4} O ₆	3.4 x 10 ^{-7*}	4.0 x 10 ⁻⁴	0.52	50 - 230	this work


* extrapolated value

ACKNOWLEDGEMENT


This work was supported in part by the Office of Naval Research, Contract N00014-82-K-0317.

REFERENCES

1. R.D. Shannon, B.E. Taylor, A.D. English and T. Berzins; *Electrochimica Acta*, 22, 783-796 (1977).
2. H.Y-P. Hong; *Mat. Res. Bull.*, 13, 117-124 (1978).
3. J.B. Goodenough, H.Y-P. Hong and J.A. Kafalas; *Mat. Res. Bull.*, 11, 203-220 (1976).
4. C. Delmas, A. Maazaz, F. Guillen, C. Fouassier, J.M. Reau and P. Hagenmuller; *Mat. Res. Bull.*, 14, 619-625 (1979).
5. J. Senegas, A.M. Villepastour and C. Delmas; *J. Solid State Chem.*, 31, 103-112 (1980).
6. R. Scholder; *Angew. Chem.*, 70, 583-614 (1958).
7. J. Hauck; *Z. Naturforsch.*, 24b, 1067-1068 (1969).
8. M.S. Whittingham and R.A. Huggins; *Solid State Chemistry* (Edited by R.S. Roth and S.J. Schneider), P. 39, Nat. Bur. Stds. Spec. Publ. 364 (1972).
9. U.V. Alpen, M.F. Bell and W. Wichelhaus; *Electrochimica Acta.*, 23, 1395-1397 (1978).



SIGNAL GENERATOR






FIG. 3




FIG. 4




FIG. 5




FIG 6




FIG. 7

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Paul Delahay Department of Chemistry New York University New York, New York 10003	1	Dr. P. J. Hendra Department of Chemistry University of Southampton Southampton SO0 5NH United Kingdom	1
Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 41106	1	Dr. Sam Perone Chemistry & Materials Science Department Laurence Livermore National Lab. Livermore, California 94550	1
Dr. D. N. Bennion Department of Chemical Engineering Brigham Young University Provo, Utah 84602	1	Dr. Royce W. Murray Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1
Dr. R. A. Marcus Department of Chemistry California Institute of Technology Pasadena, California 91125	1	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
Dr. J. J. Auburn Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. C. E. Mueller The Electrochemistry Branch Materials Division, Research and Technology Department Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910	1
Dr. Adam Heller Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. G. Goodman Johnson Controls 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. Katan Lockheed Missiles and Space Co., Inc. P. O. Box 504 Sunnyvale, California 94088	1	Dr. J. Boechler Electrochimica Corporation Attn: Technical Library 2485 Charleston Road Mountain View, California 94040	1
Dr. Joseph Singer, Code 302-1 NASA-Lewis 21000 Brookpark Road Cleveland, Ohio 44135	1	Dr. P. P. Schmidt Department of Chemistry Oakland University Rochester, Michigan 48063	1
Dr. B. Brummer EIC Incorporated 55 Chapel Street Newton, Massachusetts 02158	1		
Library P. R. Mallory and Company, Inc. Northwest Industrial Park Burlington, Massachusetts 01803	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. H. Richtol Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1	Dr. R. P. Van Duyne Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. A. B. Ellis Chemistry Department University of Wisconsin Madison, Wisconsin 53706	1	Dr. B. Stanley Pons Department of Chemistry University of Alberta Edmonton, Alberta CANADA T6G 2G2	1
Dr. M. Wrighton Chemistry Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139		Dr. Michael J. Weaver Department of Chemistry Michigan State University East Lansing, Michigan 48824	1
Larry E. Plew Naval Weapons Support Center Code 30736, Building 2906 Crane, Indiana 47522	1	Dr. R. David Rauh EIC Corporation 55 Chapel Street Newton, Massachusetts 02158	1
S. Ruby DOE (STOR) 600 E Street Providence, Rhode Island 02192	1	Dr. J. David Margerum Research Laboratories Division Hughes Aircraft Company 3011 Malibu Canyon Road Malibu, California 90265	1
Dr. Aaron Wold Brown University Department of Chemistry Providence, Rhode Island 02192	1	Dr. Martin Fleischmann Department of Chemistry University of Southampton Southampton 509 5NH England	1
Dr. R. C. Chudacek McGraw-Edison Company Edison Battery Division Post Office Box 28 Bloomfield, New Jersey 07003	1	Dr. Janet Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. A. J. Bard University of Texas Department of Chemistry Austin, Texas 78712	1	Dr. R. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. M. M. Nicholson Electronics Research Center Rockwell International 3370 Miraloma Avenue Anaheim, California	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Donald W. Ernst Naval Surface Weapons Center Code R-33 White Oak Laboratory Silver Spring, Maryland 20910	1	Mr. James R. Moden Naval Underwater Systems Center Code 3632 Newport, Rhode Island 02840	1
Dr. R. Nowak Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. Bernard Spielvogel U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709	1
Dr. John F. Houlihan Shenango Valley Campus Pennsylvania State University Sharon, Pennsylvania 16146	1	Dr. Denton Elliott Air Force Office of Scientific Research Bolling AFB Washington, D.C. 20332	1
Dr. D. F. Shriver Department of Chemistry Northwestern University Evanston, Illinois 60201	1	Dr. David Aikens Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1
Dr. D. H. Whitmore Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. A. P. B. Lever Chemistry Department York University Downsview, Ontario M3J1P3 Canada	1
Dr. Alan Bewick Department of Chemistry The University Southampton, SO9 5NH England		Dr. Stanislaw Szpak Naval Ocean Systems Center Code 6343 San Diego, California 95152	1
Dr. A. Himy NAVSEA-5433 NC #4 2541 Jefferson Davis Highway Arlington, Virginia 20362		Dr. Gregory Farrington Department of Materials Science and Engineering University of Pennsylvania Philadelphia, Pennsylvania 19104	
Dr. John Kincaid Department of the Navy Strategic Systems Project Office Room 901 Washington, D.C. 20376		Dr. Bruce Dunn Department of Engineering & Applied Science University of California Los Angeles, California 90024	

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
M. L. Robertson Manager, Electrochemical and Power Sonics Division Naval Weapons Support Center Crane, Indiana 47522	1	Dr. T. Marks Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. Elton Cairns Energy & Environment Division Lawrence Berkeley Laboratory University of California Berkeley, California 94720	1	Dr. D. Cipris Allied Corporation P. O. Box 3000R Morristown, New Jersey 07960	1
Dr. Micha Tomkiewicz Department of Physics Brooklyn College Brooklyn, New York 11210	1	Dr. M. Philpot IBM Corporation 5600 Cottle Road San Jose, California 95193	1
Dr. Lesser Blum Department of Physics University of Puerto Rico Rio Piedras, Puerto Rico 00931	1	Dr. Donald Sandstrom Washington State University Department of Physics Pullman, Washington 99164	1
Dr. Joseph Gordon, II IBM Corporation K33/281 5600 Cottle Road San Jose, California 95193	1	Dr. Carl Kannewurf Northwestern University Department of Electrical Engineering and Computer Science Evanston, Illinois 60201	1
Dr. Robert Somoano Jet Propulsion Laboratory California Institute of Technology Pasadena, California 91103	1	Dr. Edward Fletcher University of Minnesota Department of Mechanical Engineering Minneapolis, Minnesota 55455	1
Dr. Johann A. Joebstl USA Mobility Equipment R&D Command DRDME-EC Fort Belvoir, Virginia 22060	1	Dr. John Fontanella U.S. Naval Academy Department of Physics Annapolis, Maryland 21402	1
Dr. Judith H. Ambrus NASA Headquarters M.S. RTS-6 Washington, D.C. 20546	1	Dr. Martha Greenblatt Rutgers University Department of Chemistry New Brunswick, New Jersey 08903	1
Dr. Albert R. Landgrebe U.S. Department of Energy M.S. 6B025 Forrestal Building Washington, D.C. 20595	1	Dr. John Wassib Kings Mountain Specialties P. O. Box 1173 Kings Mountain, North Carolina 28086	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>	<u>No. Copies</u>
Dr. J. J. Brophy University of Utah Department of Physics Salt Lake City, Utah 84112	1	
Dr. Walter Roth Department of Physics State University of New York Albany, New York 12222	1	
Dr. Thomas Davis National Bureau of Standards Polymer Science and Standards Division Washington, D.C. 20234	1	
Dr. Charles Martin Department of Chemistry Texas A&M University	1	
Dr. Anthony Sammells Institute of Gas Technology 3424 South State Street Chicago, Illinois 60616	1	
Dr. H. Tachikawa Department of Chemistry Jackson State University Jackson, Mississippi 39217	1	
Dr. W. M. Risen Department of Chemistry Brown University Providence, Rhode Island	1	

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

ATE
LME